



**CYG-CATV**  
**Medium Wall Heat**  
**Shrinkable Tubing**  
**Adhesive-coated,**  
**Dual wall**

<ul style="list-style-type: none"> <li>◆ Non Flame Retardant</li> <li>◆ Dual Wall, Adhesive-coated. 3:1</li> <li>◆ Oval in piece</li> <li>◆ RoHS Compliant</li> <li>◆ Black Available</li> </ul>	<p><b>Features</b></p> <ul style="list-style-type: none"> <li>◆ Excellent sealing and insulating abilities</li> <li>◆ Resistant to Impact and abrasion</li> <li>◆ Continuous Working Temperature -55°C to 110°C</li> </ul>
--	--

**Technical Data :**

Property	Test Method	Typical Data
Tensile strength	ASTM D2671	≥14MPa
Elongation at break	ASTM D2671	≥400%
Elongation at break after aging	ASTM D2671/150°C, 168hrs	≥300%
Density	ASTM D792	1.05g/cm <sup>3</sup>
Eccentricity	ASTM D2671	<30%
Longitudinal shrinkage	UL224	0 to-10%
Dielectric strength	IEC243	≥20KV/mm
Volume resistivity	IEC93	≥10 <sup>14</sup> Ω.cm
Copper stability	ASTM D2671	Pass
Water absorption	ISO 62/23°C, 14 days	<0.15%

Adhesive		
Water absorption	ISO 62	<0.1%
Softening Point	ASTM-E28	85°C
Peel strength to stainless steel	ASTM D1000	110N/25mm
Copper stability	ASTM D2671	Non-corrosive
Resistance to fungus and decay	ISO 846	Pass

**Dimensions:**

Ordering Ref.	As supplied(mm)	After recovered (mm)		Standard Length (mm)	Ordering Units (Pcs/Ctn)	Package Dimensions (cm)
	Inside dia (Min.)	Inside dia (Max.)	Wall thickness (Min.)			
CYG-CATV-10/3.8	10.00	3.80	2.0	1220	500	36*36*126
CYG-CATV-19/5.6	19.00	5.60	2.4	1220	200	36*36*126
CYG-CATV-28/9	28.00	9.00	2.4	1220	125	36*36*126
CYG-CATV-33/10	33.00	10.00	2.4	1220	100	36*36*126
CYG-CATV-38/12	38.00	12.00	2.4	1220	60	36*36*126
CYG-CATV-45/13	45.00	13.00	2.4	1220	60	36*36*126
CYG-CATV- 55/19	55.00	19.00	2.4	1220	40	36*36*126
CYG-CATV-70/25	70.00	25.00	2.4	1220	30	36*36*126

Other size will be upon request.